

Australian Standard[®]

**Insulating gloves for electrical
purposes**

This Australian Standard was prepared by Committee EL/4, Electrical Accessories. It was approved on behalf of the Council of Standards Australia on 12 April 1994 and published on 14 June 1994.

The following interests are represented on Committee EL/4:

Australian Chamber of Commerce and Industry
Australian Electrical and Electronic Manufacturers Association
Consumer Electronics Suppliers Association, Australia
Electricity Supply Association of Australia
Ministry of Commerce, New Zealand
National Electrical Contractors Association of Australia
New Zealand Manufacturer's Federation
Railways of Australia Committee
Regulatory Authorities (Electrical), Australia
The Plastics Industry of Australia

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

Insulating gloves for electrical purposes

First published as AS C87—1939.
Second edition 1964 (endorsement of BS 697—1960
without amendment).
Revised and redesignated AS 2225—1978.
Second edition 1994.

Incorporating:
Amdt 1 — 1996

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee EL/4 on Electrical Accessories to supersede AS 2225—1978.

Under the terms of the Active Cooperation Agreement, this Standard is the result of a consensus among Australian and New Zealand representatives on the Joint Committee to produce this document as an Australian Standard, and the publishing of a Joint Standard will be considered during the next revision. The Committee agreed that alignment of AS 2225 with IEC 903, *Specifications for gloves and mitts of insulating material for live working*, would not be undertaken at this time. Although such alignment is a desirable long-term aim, the major reason for this revision is to allow the use of thinner and other than rubber materials, particularly for 650 V gloves.

The objective of this Standard is to provide for 650 V gloves to be more comfortable to wear and have more ‘feel’ whilst still affording adequate protection against electric shock. The four classes of gloves, viz., 650 V, 1000 V, 3300 V and 4000 V have been maintained; one minor variation being to derate the 1100 V to 1000 V, in line with the philosophy of BS 697:1986, *Specification for rubber gloves for electrical purposes*.

During the preparation of this Standard, in addition to BS 697 and IEC 903, reference was given to ASTM D 120-87, *Specification for rubber insulating gloves*.

This Standard is similar to BS 697 but differs (particularly) in the following:

- (a) No minimum thickness is specified for 650 V gloves; adequacy is determined by tests.
- (b) Specification of a 5 kV withstand test, followed by a 2.5 kV leakage current test with a 4 mA leakage allowable (for all glove lengths), for 650 V gloves. This follows a 16 h conditioning in water to determine the resistance to moisture absorption.
- (c) The test criteria remains the same as in AS 2225—1978, *Rubber gloves for electrical purposes*, for 1000 V, 3300 V and 4000 V gloves.

It should be noted that the action of Item (b) means a reduced voltage (half of that specified in AS 2225 for the leakage current test), with the allowable leakage current (specified in AS 2225 of 4 mA) being retained. This ‘reduced’ testing voltage was established after extensive tests and field trials of suitable (to the user) gloves based on the test parameters specified herein.

New tests, such as abrasion resistance, flex cracking, resistance to puncture, and tensile strength of seams, replace the mechanical tests specified in AS 2225. However, specified minimum thicknesses for 1000 V, 3300 V, and 4000 V gloves have been retained. Also, it is now mandatory for instructions for storage and cleaning to be provided with each pair of gloves.

Special attention is drawn to Appendix C which provides revised recommendations for storage and cleaning of gloves after purchase.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 CLASSIFICATION	4
5 COMPOSITION	4
6 CONSTRUCTION	4
7 DIMENSIONS	5
8 INSTRUCTIONS FOR STORAGE AND CLEANING	5
9 MARKING	5
10 TESTS	6

APPENDICES

A METHOD FOR THE DETERMINATION OF THICKNESS OF GLOVES FOR USE ON POTENTIALS ABOVE 650 V AND UP TO 4000 V	8
B TYPICAL DIMENSIONS	9
C RECOMMENDATIONS CONCERNING THE STORAGE, ISSUE, EXAMINATION BEFORE USE AND PRECAUTIONS IN THE USE OF GLOVES	11
D METHOD FOR THE DETERMINATION OF LEAKAGE CURRENT	12
E METHOD FOR TESTING RESISTANCE TO PUNCTURE	14

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Insulating gloves for electrical purposes

1 SCOPE This Standard sets out the requirements for three types of insulating gloves (as classified in Clause 4) used for electrical purposes where the working potentials do not exceed 650 V, 1000 V, 3300 V, or 4000 V (whether a.c. r.m.s., or d.c.), between any two conductors or between any conductor and earth.

NOTE: For the purposes of this Standard, the term ‘glove(s)’ applies to insulating gloves used for electrical purposes.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard.

AS

2103 Dial gauges and dial test indicators (metric series)

2161 Industrial safety gloves and mittens (excluding electrical and medical gloves)

2886 Voltage measurement—Sphere-gap method (one sphere earthed)

BS

903 Methods of testing vulcanized rubber

Part A2—Determination of tensile stress-strain properties

3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

3.1 Composite—a generic term for a combination of insulating material and other material(s), e.g. dipped, coated, sprayed, impregnated, layered or mixed.

3.2 Insulated—separated from other conducting surfaces by a dielectric substance (including air space) offering a high resistance to the passage of current.

3.3 Other than rubber—a generic term for a homogeneous insulating material of a form other than rubber as described in Clause 3.4.

3.4 Rubber—a generic term for a homogeneous material that includes elastomers and elastomeric compounds, regardless of origin.

3.5 Working voltage—the maximum use voltage, whether a.c., r.m.s. or d.c.

3.6 Routine test—a test to which each glove is subjected after manufacture.

3.7 Type test—a test performed on one or more gloves to show that the design meets the specification.

4 CLASSIFICATION Gloves are classified by the following types:

- (a) Rubber.
- (b) Other than rubber.
- (c) Composite.

5 COMPOSITION Gloves shall be made from insulating materials which comply with this Standard. A glove may contain suitable insertions which will enhance the electrical, mechanical or comfort (i.e. sensitivity) properties.

6 CONSTRUCTION Gloves, on both the inner and outer surfaces, shall be free from harmful physical irregularities that can cause hazard or significant degradation in quality or life of the glove.