

Australian Standard<sup>®</sup>

---

**Timber—Poles for overhead lines**

---

This Australian Standard was prepared by Committee TM/3, Timber Grading. It was approved on behalf of the Council of Standards Australia on 2 February 1994 and published on 18 April 1994.

---

The following interests are represented on Committee TM/3:

CSIRO, Division of Building Construction and Engineering  
Housing Industry Association  
Master Builders Australia  
National Association of Forest Industries, Australia  
New Zealand Forest Research Institute  
New Zealand Timber Industry Federation  
New Zealand Timber Suppliers Group  
University of Technology, Sydney

Additional interests participating in preparation of Standard:

Local Government Electricity Association of New South Wales

---

**Review of Australian Standards.** To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

*This Standard was issued in draft form for comment as DR 92137.*

Australian Standard<sup>®</sup>

---

**Timber—Poles for overhead lines**

---

First published as SAA Int.364—1952.  
Revised and redesignated AS O117—1970.  
Revised and redesignated AS 2209—1979.  
Second edition 1994.

Incorporating:  
Amdt 1—1997

## PREFACE

This Standard was prepared by the Standards Australia Committee TM/3 on Timber Grading to supersede AS 2209—1979, *Timber poles for overhead lines*. It was developed from a document prepared by a working group with representation from New South Wales timber pole purchaser and supplier interests which was organized by the Local Government Electricity Association of New South Wales.

The revision was undertaken because the existing document did not meet the present needs of timber pole purchasers and suppliers. In particular, its preservative treatment requirements and quality provisions did not relate to current practices.

In preparing this Standard, reference was made to AS 1604 *Timber—Preservative-treated—Sawn and round*. The procedures that it uses for specifying minimum preservative retention were adopted. The actual retentions nominated may, however, be higher for Copper Chrome Arsenic (CCA) preservatives as a consequence of the established preferences of the New South Wales electricity supply industry.

The principal changes are:

- (a) Addition of a ‘purchasing guidelines’ appendix.
- (b) Inclusion of a quality requirements clause and related appendices which provide a range of optional means for complying with its provisions.
- (c) Inclusion of clauses giving purchasers the option of asking for formal confirmation of compliance with the Standard.
- (d) Spiral grain requirements for hardwood poles.
- (e) Measurement of spiral grain by the ‘gradient’ method used for other timber products.
- (f) Reference to pentachlorophenol (PCP) has been deleted.
- (g) Emulsified form of creosote recognized.
- (h) Preservative retention specified—
  - (i) on a per pole instead of charge lot basis;
  - (ii) on both a mass/mass and mass/vol. basis with the former nominated as the ‘legal’ requirement; and
  - (iii) as active elements as well as total preservative formulation in the case of CCA.
- (i) A substantial increase in CCA retentions specified.

In addition, changes have been made to style, format and expression to accommodate current Standards Australia practice.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
<b>SECTION 1 SCOPE AND GENERAL REQUIREMENTS</b>	
1.1 SCOPE .....	5
1.2 APPLICATION .....	5
1.3 REFERENCED DOCUMENTS .....	5
1.4 DEFINITIONS .....	6
1.5 SIZE AND FORM OF POLE .....	7
1.6 PREPARATION OF POLE .....	7
1.7 MEASUREMENT OF KNOTS .....	7
1.8 NUMERICAL RATINGS FOR END SPLITS AND BARREL CHECKS .....	7
1.9 SPECIES BRANDING .....	8
1.10 DEMONSTRATING COMPLIANCE .....	8
 <b>SECTION 2 POLES INTENDED FOR USE WITHOUT FULL-LENGTH PRESERVATIVE TREATMENT</b>	
2.1 TIMBER SPECIES .....	11
2.2 GRADE DESCRIPTION .....	11
2.3 CONFIRMATION OF COMPLIANCE .....	12
 <b>SECTION 3 HARDWOOD POLES INTENDED FOR USE AFTER FULL-LENGTH PRESERVATIVE TREATMENT</b>	
3.1 TIMBER SPECIES .....	13
3.2 GRADE DESCRIPTION .....	13
 <b>SECTION 4 SOFTWOOD POLES INTENDED FOR USE AFTER FULL-LENGTH PRESERVATIVE TREATMENT</b>	
4.1 TIMBER SPECIES .....	15
4.2 GRADE DESCRIPTION .....	15
 <b>SECTION 5 REQUIREMENTS FOR FULL-LENGTH PRESERVATIVE TREATMENT</b>	
5.1 POLES FOR PRESERVATIVE TREATMENT .....	17
5.2 PRESERVATIVES .....	17
5.3 PRESERVATIVE PENETRATION .....	17
5.4 PRESERVATIVE RETENTION .....	18
5.5 DETERMINATION OF TREATMENT RESULTS .....	18
5.6 SURFACE CONDITION .....	19
5.7 CONFIRMATION OF COMPLIANCE .....	19
5.8 IDENTIFICATION .....	20
5.9 TREATMENT RECORDS .....	21
 <b>APPENDICES</b>	
A PURCHASING GUIDELINES .....	23
B TIMBER SPECIES DURABILITY CLASSIFICATIONS AND IDENTIFICATION BRANDS .....	24
C MEANS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD .....	26

	<i>Page</i>
D PRE-TREATMENT CHEMICAL TEST FOR DIFFERENTIATING BETWEEN SAPWOOD AND HEARTWOOD IN SOFTWOOD POLE TIMBERS (PANDA TEST) . . . . .	28
E EXAMPLE SYSTEMS FOR POLE TREATER PROCESS QUALITY MONITORING AND PURCHASER TREATMENT QUALITY CHECKS . . .	29

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

# STANDARDS AUSTRALIA

## Australian Standard

### Timber Poles for overhead lines

#### SECTION 1 SCOPE AND GENERAL REQUIREMENTS

**1.1 SCOPE** This Standard sets out requirements for timber poles intended primarily for use in overhead lines for electrical distribution and telecommunications purposes with or without full-length preservative treatment.

This Standard does not cover requirements for strength and dimensions and these should be separately specified.

**1.2 APPLICATION** Hardwood poles intended for use without full-length preservative treatment shall comply with the requirements of Sections 1 and 2.

Hardwood poles intended for use after full-length preservative treatment shall comply with the requirements of Sections 1 and 3.

Softwood poles intended for use after full-length preservative treatment shall comply with the requirements of Sections 1 and 4.

Any poles to be supplied after full-length preservative treatment shall also comply with all the relevant requirements of Section 5.

This Standard is intended to have general application throughout Australia but in New South Wales the Timber Marketing Act 1977, and in Queensland the Timber Utilisation and Marketing Act 1987, require prior approval of a preservative treatment and the registration and application of a brand before timber offered for sale in either of these States can be described as preservative-treated. Detailed information about the requirements of such legislation may be obtained from the State government department concerned.

This Standard requires purchasers to nominate some options and allows them to negotiate others. It also includes other guidelines for purchasers obtaining supply according to this document.

NOTE: Purchasing guidelines are given in Appendix A.

**1.3 REFERENCED DOCUMENTS** The following documents are referred to in this Standard:

AS

1080	Methods of testing timber
1080.1	Method 1: Moisture content
1143	High temperature creosote for the preservation of timber
1199	Sampling procedures and tables for inspection by attributes
1399	Guide to AS 1199—Sampling procedures and tables for inspection by attributes
1604	Timber—Preservative-treated—Sawn and round
1605	Methods for the sampling and analysis of wood preservatives and preservative-treated wood