

Australian Standard[®]

Stationary batteries — Lead-acid

Part 3: Pure lead positive pasted plate type

[Defence Title allocated by Codification and Standardisation Authority:
BATTERY (1) STORAGE
NATO Supply Classification 6140]

This Australian Standard was prepared by Committee EL/5, Secondary Batteries. It was approved on behalf of the Council of Standards Australia on 1 October 1992 and published on 15 March 1993.

The following interests are represented on Committee EL/5:

Australian Automobile Association
Australian Automotive Aftermarket Association
Australian Chamber of Commerce and Industry
Australian Electrical and Electronic Manufacturers Association
Australian Federation of Consumer Organizations
Australian Lead Development Association
Department of Defence
Electricity Supply Association of Australia
Federal Chamber of Automotive Industries
Institution of Engineers Australia
Telecom Australia

Additional interests participating in preparation of Standard:

Civil Aviation Authority
Department of Administrative Services — Australian Construction Services

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 91007.

Australian Standard[®]

Stationary batteries — Lead-acid
Part 3: Pure lead positive pasted
plate type

First published as AS 1981—1977.
Second edition 1981.
Revised and redesignated AS 4029.3—1993.

Incorporating:
Amdt 1 — 1995

PREFACE

This Standard was prepared by the Standards Australia Committee on Secondary Batteries to supersede AS 1981-1981, *Stationary batteries of the lead-acid pasted plate type*.

The major alteration to the previous edition is the classification of batteries as low, medium or high discharge rate in accordance with a specified cycle test.

Batteries of the pure lead positive plate type are usually used in applications where very high reliability and long lifespans are the major considerations of the user.

Batteries classified as low, medium or high rate were originally developed by Telecom Australia in conjunction with Australian battery manufacturers and have given service lives of from 7 to 15 years in the field.

This Standard is one of a 3-part series to cover stationary lead-acid batteries. The three parts are as follows:

- (a) A proposed Part 1 to cover vented cells.
- (b) AS 4029 *Stationary batteries - Lead-acid*
4029.2 Part 2: *Valve-regulated sealed type*.
- (c) This Standard, i.e. AS 4029.3.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

Page

SECTION 1 SCOPE AND GENERAL

| | | |
|-----|----------------------------|---|
| 1.1 | SCOPE | 4 |
| 1.2 | REFERENCED DOCUMENTS | 4 |
| 1.3 | DEFINITIONS | 4 |
| 1.4 | OPERATING CONDITIONS | 5 |
| 1.5 | MARKING | 5 |

SECTION 2 DESIGN AND CONSTRUCTION

| | | |
|------|----------------------|---|
| 2.1 | CELL ASSEMBLY | 6 |
| 2.2 | MATERIALS | 6 |
| 2.3 | CONTAINER | 6 |
| 2.4 | LIDS | 7 |
| 2.5 | SAFETY VENTS | 7 |
| 2.6 | PLATES | 7 |
| 2.7 | PLATE PASTE | 8 |
| 2.8 | GROUP BARS | 8 |
| 2.9 | CONNECTORS | 8 |
| 2.10 | TERMINAL POSTS | 8 |
| 2.11 | ELECTROLYTE | 8 |
| 2.12 | PACKAGING | 8 |

SECTION 3 PERFORMANCE REQUIREMENTS

| | | |
|-----|----------------------------|---|
| 3.1 | RATED CAPACITY | 9 |
| 3.2 | FLOAT CURRENT | 9 |
| 3.3 | SELF-DISCHARGE | 9 |
| 3.4 | CYCLE CLASSIFICATION | 9 |
| 3.5 | POST SEALS | 9 |
| 3.6 | SAFETY VENTS | 9 |
| 3.7 | INTERNAL RESISTANCE | 9 |

SECTION 4 ACCESSORIES

| | | |
|-----|------------------------|---|
| 4.1 | TOPPING-UP WATER | 9 |
| 4.2 | BOLTS AND NUTS | 9 |

SECTION 5 TEST EQUIPMENT

| | | |
|-----|----------------------|---|
| 5.1 | TEST EQUIPMENT | 9 |
|-----|----------------------|---|

APPENDICES

| | | |
|---|---|----|
| A | PURCHASING GUIDELINES | 10 |
| B | DIMENSIONS OF BATTERIES | 10 |
| C | CAPACITY TEST METHOD | 11 |
| D | FLOAT CURRENT TEST METHOD | 11 |
| E | SELF-DISCHARGE TEST METHOD | 12 |
| F | CYCLE CLASSIFICATION TEST METHOD | 13 |
| G | TEST OF POST SEALS AND COVERS | 14 |
| H | TEST OF SAFETY VENTS | 15 |
| I | INTERNAL RESISTANCE TEST METHOD | 17 |
| J | DETERMINATION OF THE DISCHARGE RATE OF PROTOTYPE OR UNTESTED BATTERIES | 17 |

STANDARDS AUSTRALIA

Australian Standard

Stationary batteries — Lead-acid

Part 3: Pure lead positive pasted plate type

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE This Standard sets out requirements for vented lead-acid batteries of the pure lead positive pasted plate type, primarily intended for use in floating service in a stationary mode.

NOTE: Appendix A gives recommendations on information to be supplied in purchasing specifications.

1.2 REFERENCED DOCUMENTS The following documents are referred to in this Standard.

AS

| | |
|---------|--|
| 1006 | Solid-stem general purpose thermometers |
| 1042 | Direct-acting indicating electrical measuring instruments and their accessories |
| 1671 | Lead and lead alloys |
| 1671.3 | Part 3: Determination of high concentrations of antimony in lead alloys containing not more than 2.5 percent arsenic and 1.0 percent copper—Titrimetric method |
| 2400 | Packaging |
| 2400.21 | Part 21: Packaging of dangerous goods |
| 2562 | Hydrometers—Portable syringe-type for lead-acid batteries |
| 2668 | Water for use in secondary batteries |
| 2669 | Sulphuric acid for use in lead-acid batteries |
| 2700 | Colour standards for general purposes |

ASTM

| | |
|-----|---|
| E37 | Method for chemical analysis of pig lead |
| E46 | Test methods for chemical analysis of lead- and tin-base solder |

1.3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

1.3.1 Accessories — items supplied with a battery to facilitate the continued operation of the battery, including distilled water, connectors and connecting nuts and bolts.

1.3.2 Battery — a unit consisting of one or more cells connected in a series, parallel, or series-parallel arrangement, to supply the voltage and current requirements of a connected load.

1.3.3 Cell — an assembly of electrodes and electrolyte which constitute the basic unit of a battery.

1.3.4 Capacity — the quantity of electricity (electric charge) usually expressed in ampere hours (A.h) which a fully charged battery can deliver under specified conditions (see Clause 1.3.5).

1.3.5 Rated capacity (rating) — the quantity of electricity in ampere hours, declared by the manufacturer which a new battery can deliver after a full charge under specified conditions of discharge rate and final voltage.

The capacity of a cell or battery is denoted by the symbol C . As the capacity varies with rate of discharge, the symbol C is followed by a numerical suffix giving the rate of discharge. Thus C_3 is the capacity in ampere hours (A.h) at the 3 h rate of discharge. The specified temperature is usually 25°C. The final voltage depends on battery type and conditions of service.

1.3.6 Available capacity — the total number of ampere hours that can be withdrawn from a cell or battery for a specific set of operating conditions including: initial state of charge, age, discharge rate, temperature and final voltage.

1.3.7 Discharge rate — the current at which a battery is discharged. This may be expressed in amperes, but more commonly it is normalized to rated capacity C and expressed as C_x .

1.3.8 Hour rate — the discharge rate of a cell or battery expressed in terms of the length of time a fully charged new cell or battery can be discharged at a specific current, before reaching a specific final voltage.

For example, if a fully charged new cell rated at 100 A.h can be discharged at 20 A for a period of 5 h before reaching its specified final voltage, then the discharge of this battery at 20 A is referred to as the 5 h rate.