

Australian Standard[®]

**Rigid cellular plastics sheets for
thermal insulation**

**Part 2: Rigid cellular
polyisocyanurate (RC/PIR)**

This Australian Standard was prepared by Committee PL/16, Rigid Cellular Plastics for Thermal Insulation. It was approved on behalf of the Council of Standards Australia on 13 December 1991 and published on 16 March 1992.

The following interests are represented on Committee PL/16:

Board of Fire Commissioners, N.S.W.

Commercial Refrigeration Manufacturers Association of Australia

CSIRO, Division of Building, Construction and Engineering

Master Builders Construction and Housing Association

Metropolitan Fire Brigades Board, Melbourne

The Plastics Institute of Australia

Railways of Australia Committee

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 91196.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 1366.2–1992

**Rigid cellular plastics sheets for thermal insulation
Part 2: Rigid cellular polyisocyanurate (RC/PIR)**

RECONFIRMATION NOTICE

Major stakeholders of this publication have reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 29 August 2018.

NOTES

Australian Standard[®]

**Rigid cellular plastics sheets for
thermal insulation**

**Part 2: Rigid cellular
polyisocyanurate (RC/PIR)**

<p>First published as AS 1366.2—1981. Second edition 1992.</p>
--

PREFACE

This Standard was prepared by the Standards Australia Committee for Rigid Cellular Plastics for Thermal Insulation under the direction of the Plastics Standards Board, to supersede AS 1366.2—1981. AS 1366, *Rigid cellular plastics sheets for thermal insulation*, has four parts, the others being as follows:

Part 1: *Rigid cellular polyurethane (RC/PUR)*

Part 3: *Rigid cellular polystyrene —Moulded (RC/PS—M)*

Part 4: *Rigid cellular polystyrene —Extruded (RC/PS—E)*

The products covered by this Standard are mainly intermediate products used as insulants, either by their manufacturer or by another manufacturer, in the production of thermal insulation products (e.g. building panels, cool store panels, insulation for bulk containers).

Density has been used over a number of years as a means of classifying cellular plastics. Because of advances in technology, similar physical characteristics may be achieved by materials of different apparent density; for this reason the density of the material is not included in the list of specified physical properties.

The subsequent processing of the sheets is the determining factor in the fire hazard associated with the use of these materials (i.e. the potential for harm to life or property resulting from the occurrence of a fire). For example, when used in buildings, cellular plastics may need to be faced with lining materials in order to achieve adequate fire performance. Thus it is not relevant to include a fire performance test for the materials specified in this Standard. The users of these materials should apply suitable fire performance tests to products in their finished form. Purchasers of products fabricated from these materials should specify such tests in their purchasing agreements. For building structures and components, suitable tests are described in AS 1530, *Methods for fire tests on building materials, components and structures*, Part 3: *Simultaneous determination of ignitability, flame propagation, heat release and smoke release* and Part 4: *Fire resistance test of elements of building construction*.

A combustion characteristics test has been included; however, it must be emphasized that a combustion characteristics test gives no indication of the fire hazard associated with the use of the sheet, but is used to compare relative combustion properties of the material. The test has been included to ensure a specified minimum level of fire retardancy in the sheet.

Reference should be made to AS 2627, *Thermal insulation of dwellings—Design guide*, for installation of thermal insulation in domestic dwellings and for guidance on correct placing of vapour barriers for protection in situations where temperature differentials may occur. For industrial and commercial applications, expert advice should be sought.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 COLOUR	4
5 APPEARANCE	4
6 DIMENSIONS AND FINISH	4
7 TEST SPECIMENS	5
8 SAMPLING AND CONDITIONING	6
9 PHYSICAL PROPERTIES	6
10 DETERMINATION OF FLAME PROPAGATION	6
11 MARKING	6

APPENDICES

A METHODS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	7
B EFFECTS OF AGEING ON THERMAL RESISTANCE	8

STANDARDS AUSTRALIA

Australian Standard
Rigid cellular plastics sheets for thermal insulation

Part 2: Rigid cellular polyisocyanurate (RC/PIR)

1 SCOPE This Standard specifies requirements for rigid cellular polyisocyanurate (RC/PIR) in the form of sheets, board, blocks and cut shapes for thermal insulation purposes. These requirements are intended for use in quality control and material specification, and are not necessarily applicable for end use design requirements.

NOTE: Alternative methods for determining compliance with this Standard are given in Appendix A.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS	
1199	Sampling procedures and tables for inspection by attributes
1399	Guide to AS 1199—Sampling procedures and tables for inspection by attributes
2122	Combustion propagation characteristics of plastics
2122.1	Part 1: Determination of flame propagation following surface ignition of vertically oriented specimens of cellular plastics
2464	Methods of testing thermal insulation
2464.5	Method 5: Steady-state thermal transmission properties by means of the heat flow meter
2464.6	Method 6: Steady-state thermal transmission properties by means of the guarded hotplate
2498	Methods of testing rigid cellular plastics
2498.1	Method 1: Sampling and conditioning
2498.3	Method 3: Determination of compressive stress
2498.5	Method 5: Determination of water vapour transmission rate
2498.6	Method 6: Determination of dimensional stability
2498.7	Method 7: Determination of volume percentage of open and closed cells
2498.8	Method 8: Determination of water absorption
2900	Quantities, units, and symbols
2900.4	Part 4: Quantities and units of heat
3900	Quality systems—Guide to selection and use
3904	Quality management and quality system elements
SAA	
HB 18	Guidelines for third-party certification and accreditation
HB 18.44	General rules for ISO or IEC international third-party certification schemes for products
ISO	
7850	Cellular plastics, rigid—Determination of compressive creep

3 DEFINITIONS For the purposes of this Standard, the definitions below apply.

3.1 Rigid cellular plastics sheet—a rectangular flat slab of cellular plastics material of definite uniform thickness.

3.2 Rigid cellular polyisocyanurate (RC/PIR)—a cellular material produced under specific conditions by the trimerization of a polymeric di-isocyanate in the presence of a minor amount of a polyhydroxyl compound expanded with a blowing agent.

3.3 Thermal resistance*—a measure of the thermal properties of building materials, measured in square metre kelvin per watt ($\text{m}^2\text{K}/\text{W}$).

4 COLOUR The colour of rigid cellular polyisocyanurate (RC/PIR) should be orange.

NOTES:

- 1 This colour is intended to indicate that the RC/PIR complies with the requirements of this Standard, in particular those for flame propagation.
- 2 The purchaser may specify another colour.

5 APPEARANCE There are a number of properties such as uniformity of cell structure, homogeneity, splits, streaks and discoloration which cannot be sensibly quantified.

NOTE: Where any of these are considered to be important, arrangements should be made between purchaser and supplier.

6 DIMENSIONS AND FINISH

6.1 Rough shapes Rough shapes shall be finished to specified dimensions.

NOTE: Dimensions are a matter for agreement between the purchaser and the supplier.

6.2 Cut shapes Cut shapes shall be finished to the specified size and in accordance with the particular application.

NOTE: Size is a matter for agreement between the purchaser and the supplier.

* In AS 2900.4, 'thermal resistance' is called 'thermal insulance' with the symbol M.