

Australian Standard[®]

Adhesives for timber and timber products

Part 2: Polymer emulsion adhesives

[Title allocated by Defence Cataloguing Authority: ADHESIVES
(Timber and timber products) NSC 8040]

This Australian Standard was prepared by Committee CH/17, Adhesives. It was approved on behalf of the Council of Standards Australia on 31 January 1991 and published on 15 April 1991.

The following interests are represented on Committee CH/17:

Adhesives and Sealants Manufacturers Association of Australia
Chemical Confederation of Australia
Confederation of Australian Industry
CSIRO, Division of Building, Construction and Engineering
Footwear Manufacturers Association of Australia
Plywood Association of Australia
Printing and Allied Trades Employers Federation of Australia
Society of Automotive Engineers—Australasia
Telecom Australia

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 89158.

Australian Standard[®]

Adhesives for timber and timber products

Part 2: Polymer emulsion adhesives

First published as AS 2370—1980.
Revised and redesignated AS 2754.2—1991.

PREFACE

This Standard was prepared by the Standards Australia Committee on Adhesives under the direction of the Chemical Standards Board to supersede AS 2370—1980, PVAC Emulsion Adhesives for Wood.

This Standard constitutes Part 2 of a series of Standards for adhesives for timber and timber products. Part 1 deals with adhesives for plywood manufacture, whereas Part 3 deals with adhesives for nonstructural applications.

In this edition polymer emulsion adhesives are designated Types 1 to 5 according to their suitability for use, i.e. how well they may retain their bond strength over time under different conditions. Also, a water-soak/conditioning treatment prior to shear strength testing has been included.

 CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 CLASSIFICATION	3
5 SAMPLING	3
6 TEST CONDITIONS	3
7 PRODUCT CHARACTERISTICS	3
8 PACKAGING	5
9 MARKING	5
10 PRODUCTION INFORMATION	5
APPENDICES	
A METHOD FOR DETERMINING MINIMUM FILM-FORMING TEMPERATURE	6
B METHOD OF TEST FOR STAINING	9

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Adhesives for timber and timber products

Part 2: Polymer emulsion adhesives

1 SCOPE This Standard specifies requirements for polymer emulsion adhesives, in one-component and two-component preparations, intended for wood-to-wood bonding.

NOTE: The Standard is applicable to polymer emulsion adhesives which are prepared by emulsion polymerization of specific monomers with water as the continuous phase.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- 1309 Glossary of terms used in the adhesives industry
1321 Methods for the sampling and testing of adhesives
1321.1 Part 1: Sampling
1321.3 Part 3: Bond strength of cured wood-to-wood adhesives in shear
1321.4 Part 4: Wearing effect of set adhesives on cutting edges
1321.5 Part 5: Behaviour of cured wood-to-wood adhesives under long-term loading
1321.7 Part 7: pH value of aqueous extracts of uncured adhesives and of their components, and of cured adhesive films
1321.9 Part 9: Brookfield viscosity of liquid adhesives
1321.10 Part 10: Determination of non-volatile matter (solids content) of adhesives

ISO

- 2115 Plastics—Aqueous dispersions of polymers and copolymers—Determination of white point temperature and minimum film-forming temperature

3 DEFINITIONS For the purpose of this Standard, the definitions given in AS 1309 and those below apply.

3.1 White point temperature—the limiting temperature below which an opaque mass and above which a transparent film are formed.

3.2 Minimum film-forming temperature the limiting temperature above which a continuous homogeneous film without cracks is formed.

4 CLASSIFICATION Polymer emulsion adhesives are classified according to their suitability for use over a long period under different environmental conditions. On this basis the adhesives are designated as follows:

Type 1 Adhesive—Suitable for full weather exposure, or exposure to continuous or intermittent wet internal environments, in non-structural applications.

Type 2 Adhesive—Suitable for protected external environmental exposure with high humidity and with intermittent wetting, e.g. external doors and windows, in non-structural applications.

Type 3 Adhesive—Suitable for interior use with high humidity and with occasional wetting, e.g. bathroom, kitchen and laundry.

Type 4 Adhesive—Suitable for interior use with high humidity, e.g. an internal tropical climate.

Type 5 Adhesive—Suitable for interior use with low humidity, e.g. doors, furniture and panelling.

5 SAMPLING Selection of the adhesive sample shall be in accordance with AS 1321.1.

6 TEST CONDITIONS Unless otherwise specified, all mixing and tests on the adhesive shall be carried out at a temperature of $23 \pm 2^\circ\text{C}$ and a relative humidity of 50 ± 5 percent. The adhesives shall be used and mixed exactly as prescribed by the supplier.

7 PRODUCT CHARACTERISTICS

7.1 Uniformity The adhesive shall be uniform, smooth and free from coarse particles. The adhesive shall be suitable for the required method of application.

7.2 Viscosity When tested in accordance with AS 1321.9, the adhesives shall have a Brookfield viscosity within the range specified by the supplier.