

Australian Standard[®]

Hand hammers

**Part 2: Specific requirements for
heavy hammers**

This Australian Standard was prepared by Committee ME/10, Small Tools. It was approved on behalf of the Council of Standards Australia on 24 July 1990 and published on 11 February 1991.

The following interests are represented on Committee ME/10:

Australian British Chamber of Commerce
Austroads
Confederation of Australian Industry
CSIRO, Division of Manufacturing Technology
Deakin University
Department of Defence
Department of Technical and Further Education, New South Wales
Fasteners Institute of Australia
Metal Trades Industry Association of Australia
Railways of Australia Committee
Telecom Australia
The Workcover Authority, New South Wales

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 88170.

Australian Standard[®]

Hand hammers

**Part 2: Specific requirements for
heavy hammers**

First published as AS 3797.2—1991

PREFACE

This Standard was prepared by the Standards Australia Committee on Small Tools. It is one of a series of three Standards for hand hammers. The other Standards in the series deal with general requirements for hand hammers and specific requirements for light hammers.

In the preparation of this Standard consideration was given to BS 876, *Hand hammers*, and ANSI B173.3, *Safety requirements for heavy striking tools*, and acknowledgment is made of the assistance therefrom.

An appendix to the Standard sets out recommendations for safety requirements and limitations on the use of heavy hand hammers.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 APPLICATION	3
3 REFERENCED DOCUMENTS	3
4 DEFINITIONS	3
5 CLASSIFICATION OF DOUBLE-FACED SLEDGE-HAMMERS	3
6 MATERIALS	3
7 MANUFACTURING REQUIREMENTS AND HEAT TREATMENT	3
8 FINISH	3
9 PERFORMANCE REQUIREMENTS	3
10 MARKING	4
 APPENDICES	
A DESIGNS AND NOMENCLATURE OF HEAVY HAND HAMMERS	5
B SAFETY REQUIREMENTS AND LIMITATIONS OF USE OF HEAVY HAND HAMMERS	7

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Hand hammers

Part 2: Specific requirements for heavy hammers

1 SCOPE This Standard specifies requirements for the design, construction, and testing of heavy hand hammers intended for heavy striking of wood, metal, concrete, masonry, or stone and for double-handed use.

General requirements for hand hammers are specified in AS 3797.1.

Designs and nomenclature of heavy hand hammers are shown in Appendix A.

NOTE: Recommendations for the safe use of heavy hand hammers are given in Appendix B.

2 APPLICATION Heavy hand hammers shall comply with the applicable requirements of AS 3797.1 and the particular requirements of this Standard.

NOTE: Heavy hand hammers of types not specifically defined herein should comply with the applicable requirements of this Standard and AS 3797.1.

3 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

1337 Eye protectors for industrial applications

3797 Hand hammers

3797.1 Part 1: General requirements

4 DEFINITIONS For the purpose of this Standard, the definitions given in AS 3797.1 apply.

5 CLASSIFICATION OF DOUBLE-FACED SLEDGE-HAMMERS Double-faced sledge-hammers shall be classified by hardness of striking faces. (See Clause 7.2.3.)

6 MATERIALS Materials for heavy hand hammers shall comply with AS 3797.1.

7 MANUFACTURING REQUIREMENTS AND HEAT TREATMENT

7.1 Design and construction The design and construction of heavy hand hammers shall comply with AS 3797.1.

7.2 Heat treatment

7.2.1 General The heat treatment of heavy hand hammers shall comply with AS 3797.1 and with the requirements of Clause 7.2.2.

7.2.2 Hardness of fullering surfaces and scoring edges The hardened zone of the peens of stone sledge-hammers and blacksmith's cross-peen sledge-hammers, and similar hammers, when measured from the fullering surface or scoring edge shall extend to a minimum depth of 12 mm at which depth the hardness shall not be less than 460 HV 30 (46HRC) and not more than that at the surface.

7.2.3 Hardness of double faced sledge-hammers The hardness of double-faced sledge-hammers shall be as follows:

(a) *General temper*

(i) Striking faces 480 HV 30 to 640 HV 30 (48 HRC to 58 HRC)

(ii) Core 460 HV 30 (46 HRC)

(b) *Temper A*

(i) Striking faces 450 HV 30 to 510 HV 30 (45 HRC to 50 HRC)

(ii) Core 450 HV 30 (42 HRC)

(c) *Temper B*

(i) Striking faces 590 HV 30 to 680 HV 30 (55 HRC to 60 HRC)

(ii) Core 510 HV 30 (50 HRC)

8 FINISH The finish of heavy hand hammers shall comply with the requirements of AS 3797.1.

9 PERFORMANCE REQUIREMENTS

9.1 General Heavy hand hammers shall comply with the requirements of AS 3797.1 and the requirement of Clause 9.2.