AS 3899—1991

Australian Standard®

Higher rank coal and coke—Bulk density

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 22 April 1991 and published on 10 June 1991.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy Australian Coal Association Australian Coal Industry Research Laboratories Australian Coal Preparation Society Australian Institute of Energy Bureau of Steel Manufacturers of Australia Confederation of Australian Industry CSIRO, Division of Coal and Energy Technology Department of Resource Industries, Qld Electricity Supply Association of Australia Institution of Engineers, Australia Joint Coal Board National Association of Testing Authorities, Australia Queensland Coal Board Royal Australian Chemical Institute Standing Committee on Coalfield Geology of New South Wales University of New South Wales University of Queensland

This Standard was issued in draft form for comment as DR 89105.

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

AS 3899-1991

Australian Standard®

Higher rank coal and coke—Bulk density

First published as AS 3899-1991.

PUBLISHED BY STANDARDS AUSTRALIA (STANDARDS ASSOCIATION OF AUSTRALIA) 1 THE CRESCENT, HOMEBUSH, NSW 2140

PREFACE

This Standard was prepared by the Standards Australia Subcommittee on Coal Preparation, under the supervision of the Committee on Coal and Coke and the direction of the Minerals Standards Board.

The hopper-filled box method and the uncompacted box method for the determination of bulk density of higher rank coal are new methods.

The measuring cylinder method for higher rank coal has been transferred from AS 1038.12.2—1980, *Methods for the analysis and testing of coal and coke*, Part 12.2: *Assessment of coking power of hard coal: Gray-King coke type test*, which has been revised.

The method for the determination of the bulk density of coke has been transferred from AS 1038.13—1976, *Methods for the analysis and testing of coal and coke*, Part 13: *Tests special to coke*, which has been revised.

CONTENTS

Daga

		Tuge
FORE	EWORD	3
1	SCOPE	4
2	REFERENCED DOCUMENTS	4
3	DEFINITIONS	4
4	DETERMINATION OF BULK DENSITY OF HIGHER RANK COAL	4
5	DETERMINATION OF BULK DENSITY OF COKE	9
6	CALCULATION OF RESULTS	9
7	ACCEPTANCE OF RESULTS	10
8	REPORTING OF RESULTS	10
9	PRECISION OF THE DETERMINATIONS	10
10	TEST REPORT	10

© Copyright - STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

FOREWORD

The bulk density of coal depends upon its physical characteristics, i.e. apparent relative density and shape of particles, the dimensions of the container, the size distribution of the coal particles and their moisture content.

Results for bulk density will change according to variations in the above characteristics. In practice, results can be considered under three main headings:

- (a) As *poured*—the bulk density that results from pouring the material into a heap or container in the absence of compacting forces.
- (b) *Compacted*—the bulk density created by the application of compacting forces, e.g. impact or vibration.
- (c) *Aerated**—the bulk density created when particles are separated from each other by an air film. (Applies only to fine, dry powders.)

In any bulk density measurement, the test conditions should simulate or represent, as closely as possible, the actual conditions under which the bulk density needs to be known, as the method used will influence the result[†]. The method used to determine bulk density has to be specified in the test report.

^{*} A brief description of this procedure is given in *Bulk solids physical properties test guide*, British Materials Handling Board, 1983.

[†] CSIRO Report TC 19, The control of bulk density by moisture and oil addition, August 1957.

STANDARDS AUSTRALIA

Australian Standard

Higher rank coal and coke—Bulk density

1 SCOPE This Standard sets out methods for the determination of the bulk density of crushed higher rank coal and coke.

Three methods are described for the determination of the bulk density of higher rank coal, viz.:

- (a) Hopper-filled box method, for coal less than 5.6 mm nominal top size, applicable to crushed coals to be used as coke oven feed.
- (b) Uncompacted box method, for coal less than 45 mm nominal top size (see Note to Clause 4.3.3(a)).
- (c) Measuring cylinder method, for coal typically less than 63 μm, as used in pulverized fuel-fired boilers and cement kilns.

2 **REFERENCED DOCUMENTS** The following documents are referred to in this Standard:

AS

- 1038 Methods for the analysis and testing of coal and coke
- 1038.1 Part 1: Total moisture in hard coal
- 1038.2 Part 2: Total moisture in coke
- 1038.12.2 Part 12.2: Carbonization properties of higher rank coal—Determination of Gray-King coke type
- 1038.13 Part 13: Tests specific to coke
- 2096 Classification and coding systems for Australian coals
- 2646 Sampling of solid mineral fuels
- 2646.2 Part 2: Hard coal—Sampling from moving streams
- 2646.3 Part 3: Coke—Sampling from moving streams
- 2646.4 Part 4: Hard coal—Sampling from stationary situations
- 2646.5 Part 5: Coke—Sampling from stationary situations
- 2646.6 Part 6: Hard coal—Preparation of samples
- 2646.7 Part 7: Coke—Preparation of samples
- 2706 Numerical values—Rounding and interpretation of limiting values

3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

3.1 Bulk density of higher rank coal—the mass of a unit volume of higher rank coal, including the voids within and between the particles, measured under standard conditions.

3.2 Bulk density of coke—the mass per unit volume of dry coke, as determined in a standard container using a standardized procedure.

NOTE: The preferred unit for bulk density of coke is kilograms per cubic metre.

3.3 Higher rank coal (as defined in AS 2096)—coal having a gross specific energy of 21.00 MJ/kg or greater on an ash-free, moist basis *and* 27.00 MJ/kg or greater on a dry, ash-free basis.

4 DETERMINATION OF BULK DENSITY OF HIGHER RANK COAL

4.1 General Samples containing fines will show significant variations in bulk density with variations in moisture. Care should be taken to ensure that moisture in the test sample is representative of the gross sample.

4.2 Hopper-filled box method*

4.2.1 Principle The bulk density is measured after dropping a coal sample from a small, fixed height into a weighed box of known volume, and then determining the mass of coal required to fill the box completely.

- **4.2.2** *Samples* Samples required are as follows:
- (a) *Gross sample* Coal samples shall be collected in accordance with AS 2646.2 or AS 2646.4. During the collection of the gross sample, the increments of the sample shall be stored in an air-tight container to prevent loss of moisture. The minimum mass of sample for bulk density shall be 150 kg—sufficient for four replicate determinations and for the concurrent determination of size analysis and total moisture.

^{*} The results from this method are comparable with those using ASTM D 291—*Cubic foot weight of crushed bituminous coal*—*Procedure A.*