

Australian Standard[®]

Steel wire ropes

This Australian Standard was prepared by Committee ME/7, Steel Wire Ropes. It was approved on behalf of the Council of Standards Australia on 16 June 1988 and published on 20 October 1989.

The following interests are represented on Committee ME/7:

Australasian Institute of Mining and Metallurgy
Australian Chamber of Commerce
Australian Chamber of Shipping
Australian Federation of Construction Contractors
Australian Mining Industry Council
Confederation of Australian Industry
Department of Defence
Department of Industrial Relations & Employment, N.S.W.
Lift Manufacturers Association of Australia
Telecom Australia.

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 86001.

Australian Standard[®]

Steel wire ropes

For previous history see Preface.
AS 1426—1973 and AS 1656—1974 revised, amalgamated
and redesignated AS 3569—1989.

PREFACE

This Standard was prepared by the Standards Australia Committee on Steel Wire Ropes to supersede AS 1426—1973, *Steel wire ropes for winding and haulage purposes in mines*, and AS 1656—1974, *Steel wire ropes (other than for mining purposes)*.

The first Australian Standard for steel wire ropes, viz AS B9, *Round steel wire ropes for cranes and hoists*, was issued in 1938 and revised and redesignated AS B 185 in 1968.

In 1955, AS M4, *Steel wire ropes for winding and haulage purposes in mines*, was issued. This Standard was revised and metricated as AS 1426 in 1973.

In addition, the following Standards were produced in 1968:

AS B183 *Steel wire ropes for general purposes*

AS B184 *Steel wire ropes for lifts*

AS B186 *Steel wire ropes for field equipment*

AS B187 *Galvanized steel wire ropes for marine and other purposes*.

In 1974, AS B183 to AS B187 inclusive were revised and metricated and issued as AS 1656.

The Standard now covers steel wire ropes used for general purposes, for lifts, and for mine winding and haulage purposes. In addition to amalgamating AS 1426 and AS 1656 it has been expanded to include ropes not previously listed. Ropes no longer used have been deleted. The International (ISO) system of rope designation has been adopted.

The committee has suggested that the introduction of the ISO designation system be phased in over a period of two years. This time period is a matter for the industry to decide but, to assist in converting from the present Australian method to the ISO System, charts are included in which the constructions are labelled in the three systems, namely, the ISO construction, the abbreviated ISO construction, and the previous Australian Standard construction. As a further aid, charts are also included which give the method of describing the ISO designation system. The charts are not copyright so they may be reproduced for use as wallcharts or in other suitable ways for education or reference.

Appendices have been added which provide information to be supplied by purchasers, guidelines on the selection of ropes, examples of typical rope applications, method of calculating the minimum breaking force, and the previous Australian Standard rope designation system.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1. SCOPE AND GENERAL	
1.1 SCOPE	5
1.2 REFERENCED DOCUMENTS	5
1.3 DEFINITIONS	5
SECTION 2. ROPE DESIGNATIONS	
2.1 DESIGNATION	8
2.2 SIZE	8
2.3 SURFACE FINISH OF THE WIRES	8
2.4 ROPE CONSTRUCTION	8
2.5 GRADE OF ROPE	9
2.6 DIRECTION OF LAY	11
2.7 MINIMUM BREAKING FORCE OF ROPE	11
2.8 LINEAR MASS	11
2.9 EXAMPLES OF ROPE DESIGNATIONS	11
2.10 TABLES OF LINEAR MASS AND BREAKING FORCE	16
SECTION 3. MATERIALS	
3.1 WIRE	40
3.2 WIRE GRADE	40
3.3 FIBRE CORES	40
3.4 LUBRICANTS	40
3.5 GALVANIZING	40
SECTION 4. MANUFACTURE	
4.1 CORE OF ROPES	41
4.2 CORE OF STRANDS	41
4.3 DIRECTION OF LAY OF ROPE	41
4.4 FORMING	41
4.5 LUBRICATION	41
4.6 JOINTS	41
4.7 FREEDOM FROM DEFECTS AFTER MANUFACTURE	41
4.8 FINISHED DIMENSIONS	41
4.9 MASS OF ROPE	42
SECTION 5. MARKING AND PACKING	
5.1 MARKING	43
5.2 WHIPPING	43
5.3 PACKING	43
SECTION 6. TEST REQUIREMENTS	
6.1 TESTS ON COMPLETED ROPE	44
6.2 TESTS ON WIRES FROM ROPE	44
6.3 REPEAT TESTS	45
6.4 ADDITIONAL TESTS	45
6.5 TEST CERTIFICATES	45

APPENDICES

A	PURCHASING GUIDELINES	46
B	GUIDELINES FOR ROPE SELECTION	52
C	LOCKED AND HALF-LOCKED COIL ROPES	59
D	CALCULATION OF STEEL WIRE ROPE BREAKING FORCE . . .	61
E	PREVIOUS STEEL WIRE ROPE DESIGNATION SYSTEM	62

CHARTS (REDUCED)

1	STEEL WIRE ROPES—DESIGNATION—GENERAL CASE	64
2	STEEL WIRE ROPES—DESIGNATION—SPIRAL STRAND AND LOCKED COIL ROPE	65
3	STEEL WIRE ROPES—DESIGNATION—STRANDED ROPE	66
4	STEEL WIRE ROPES—DESIGNATION—BRAIDED ROPE	67
5.1	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	68
5.2	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	69
5.3	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	70
5.4	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	71
5.5	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	72
5.6	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	73
5.7	STEEL WIRE ROPES—EXAMPLES OF CONSTRUCTION, FULL, ABBREVIATED AND SUPERSEDED	74

STANDARDS AUSTRALIA

Australian Standard
Steel wire ropes

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This Standard specifies requirements for steel wire ropes.

NOTE: Guidelines are given in Appendix A for the purchasing of ropes and in Appendix B for rope selection. Appendix E sets out the previous designation method. For guidance on recommended procedures for the selection, storage, handling maintenance, use, inspection, and discard of helically laid steel wire ropes, see AS 2759.

1.2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

AS

1394	Round steel wire for ropes
1821	Suppliers quality systems for design, development production and installation
1822	Suppliers quality systems for production and installation
1823	Suppliers quality inspection systems
2000	Guide to AS 1821-1823—Suppliers quality control systems
2193	Methods for calibration and grading of force-measuring systems of testing machines
2759	Steel wire rope—Application guide
ISO	
3578	Steel wire ropes—Standard designations
BS	
525	Fibre cores for wire ropes
NCB	
186	Locked coil winding ropes
388	Half locked coil guide ropes

1.3 DEFINITIONS. For the purpose of this Standard, the definitions below apply.*

1.3.1 Bright wire (NAT)—ungalvanized wire.

1.3.2 Closing—laying strands together to form a rope.

1.3.3 Core.

- (a) *Core of strand*—the central member of a strand which may be one of the following (see also Figure 1.2):
- (i) A single wire (king wire).
 - (ii) A group of wires.
 - (iii) A synthetic or natural material.
- (b) *Core of rope*—the centre core of the rope around which the strands are laid. This may be one of the following:
- (i) A wire strand core (IWS).
 - (ii) A wire rope core (IWR).
 - (iii) A fibre core (FC, NFT, SF).

1.3.4 Filler wire—wire used primarily for the spacing and support of the main wires in a strand, to allow for parallel laying of strand wires in one operation.

1.3.5 Galvanized (zinc-coated) rope—rope manufactured from zinc-coated wire complying with AS 1394.

1.3.6 Grade of rope—a number which corresponds to the value of the minimum tensile strength, in megapascals (MPa), of the outside wires of the rope.

NOTE: For ropes containing wires of various tensile strengths, each strength should be nominated.

1.3.7 Grade of wire—the minimum value of the tensile strength of the wire in megapascals (MPa), expressed as a number.

1.3.8 Lay—the manner, direction, and pitch in which the strands are laid around the centre of a rope, or in which the wires are laid around the centre of a strand.

1.3.9 Lay direction—

- (a) *Left-hand*—the direction of lay as viewed which is in the same direction as the central part of the letter 'S' when the rope or strand is supported vertically. See Figure 1.4.
- (b) *Right-hand*—the direction of lay as viewed which is in the same direction as the central part of the letter 'Z' when the rope or strand is supported vertically. See Figure 1.4.

1.3.10 Lay length—that distance in a strand or rope measured parallel to the longitudinal axis, in which the wire in the strand or the strand in the rope makes one complete turn (helix) about the axis of the strand or rope.

1.3.11 Lay, Lang's—a rope construction with the strands in the rope laid in the same direction as the outer layer of wires in the strands. See Figure 1.4.

1.3.12 Lay, ordinary—a rope construction with the strands in the rope laid in the opposite direction to the outer layer of wires in the strand. See Figure 1.4.

1.3.13 Layer—a group of strands in a rope, or a group of wires in a strand, laid consecutively around the core.

1.3.14 Minimum breaking force—the tensile force which a sample of the rope must withstand without breaking when loaded in the prescribed manner.

1.3.15 Multilayer stranded rope—rope with two or more layers of main rope strands laid around a core.

1.3.16 Nominal diameter—the diameter used for purposes of description.

1.3.17 Non-rotating rope—rope in which various layers of strands are laid right-hand and left-hand to minimize resultant torque.

* The letters in parenthesis (round brackets) after certain terms are the designation in accordance with Section 2.