

AS 1565—1996
Reconfirmed 2020

Australian Standard[®]

**Copper and copper alloys—
Ingots and castings**

This Australian Standard was prepared by Committee MT/2, Copper and Copper Alloys. It was approved on behalf of the Council of Standards Australia on 17 May 1996 and published on 5 September 1996.

The following interests are represented on Committee MT/2:

AUSTAP

Australian Foundry Institute

Hunter Water Corporation, Australia

Metal Trades Industry Association of Australia

New Zealand Manufacturers Federation

Welding Technology Institute of Australia

Additional interests participating in preparation of Standard:

Non-ferrous foundries

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 95207.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 1565—1996

Copper and copper alloys—Ingots and castings

RECONFIRMATION NOTICE

Technical Committee MT-002 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 18 November 2020.

The following are represented on Technical Committee MT-002:

Weld Australia

International Copper Association Australia

Consumer Electronics Suppliers Association

Australian Institute of Refrigeration Air Conditioning and Heating

Australian Industry Group

NOTES

AS 1565—1996

Australian Standard[®]

**Copper and copper alloys—
Ingots and castings**

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7337 0624 X

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee MT/2, Copper and Copper Alloys, to supersede AS 1565—1985. The grades of copper and copper alloys and their compositions have been revised so that they align with the current listing of the Unified Numbering System designations.

This Standard is the result of a consensus among Australian and New Zealand representatives on the Joint Committee to produce it as an Australian Standard.

No International (ISO) Standards are available on the subject of copper and copper alloy ingots and castings.

The objective of this Standard is to specify the requirements for the manufacture and testing of copper and copper alloy ingots and castings.

Statements expressed in mandatory terms in notes to tables are deemed to be requirements of this Standard.

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITION	4
4 DESIGNATION	5
5 MATERIALS	5
6 FREEDOM FROM DEFECTS	6
7 TEST PROCEDURES AND REQUIREMENTS	6
8 ROUNDING OF TEST RESULT VALUES	7
9 MARKING	7
 APPENDICES	
A PURCHASING GUIDELINES	15
B CODING SYSTEM WHEN ADDITIONAL INSPECTION IS REQUIRED FOR CASTINGS	19
C RELATED COMPOSITION SPECIFICATIONS	22
D COLOUR CODE FOR INGOTS	23
E SHAPES OF STANDARD TEST BARS	24
F A GUIDE TO ALLOY SELECTION	26

Originated as AS H13—1940 and AS H14—1940.
 Previous edition AS 1565—1985.
 Third edition 1996.

STANDARDS AUSTRALIA

Australian Standard

Copper and copper alloys—Ingots and castings

1 SCOPE This Standard specifies requirements for the manufacture and testing of high conductivity copper castings and copper alloy ingots and castings.

NOTES:

- 1 Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in Appendix A.
- 2 Provision has been made for additional inspection requirements for castings which can be specified by a coding system (see Appendix B).

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- 1391 Methods for tensile testing of metals
- 1515 Copper alloys (all parts)
- 1696 Copper
- 1696.1 Part 1: Determination of phosphorus—Spectrophotometric method
- 1816 Metallic materials—Brinell hardness test
- 2062 Methods for non-destructive penetrant testing of products and components
- 2345 Dezincification resistance of copper alloys
- 2614 Copper and copper alloys—Sampling for chemical analysis and electrical resistivity
- 2700 Colour standards for general purposes
- 2706 Numerical values—Rounding and interpretation of limiting values
- 2883 Analysis of metals—Procedures for the setting up, calibration and standardization of atomic emission spectrometers using arc/spark discharge
- 3641 Recommended practice for atomic emission spectrometric analysis
- 3641.1 Part 1: Principles and techniques
- K208 Methods for the analysis of unalloyed copper
- K208.1 Part 1: Method for the electrolytic determination of copper in unalloyed copper containing not less than 99.85 percent copper

BS

- 5714 Method of measurement of resistivity of metallic materials

ASTM

- E 53 Test methods for chemical analysis of copper

3 DEFINITION For the purpose of this Standard the definition below applies.

3.1 Cast—the product of one furnace melt, one crucible melt, or a number of furnace or crucible melts that are aggregated and mixed prior to sampling.

NOTE: In respect to continuous melting for the production of castings, a 'cast' is defined as 500 kg of melted metal.